

T-FIT®

Hygiene Flex


Insulation tailored for FMCG production processes

T-FIT® Hygiene Flex is manufactured from Zotefoams ZOTEK® closed cell PVDF foam. The values provided in this Product Information Sheet represent data gathered from random samples of our production of ZOTEK Flat Sheets from which T-FIT Hygiene Flex is produced and represent typical data. These are given to the best of our knowledge and should be considered as guidance only for selecting a suitable grade for a given application.

Typical Values

Property	Test Standard	Typical Value
Material		ZOTEK PVDF
 Service Temperature	*See Notes Below	-80 to 110 °C (-112°F to +230 °F)
 Thermal Conductivity Mean temperature of 10°C (50°F) Mean temperature of 25°C (77°F) Mean temperature of 40°C (104°F) Mean temperature of 60°C (140°F)	ISO 8301	0.032 0.034 0.036 0.039
 Fire Testing Euroclass	EN13501-1 Thickness: 6.35-12.7mm	B - s1, d0
 Water Vapour Transmission	ISO 1663:2007(E)	8940 µ Value
 Fungus Resistance	ASTM G21-15	Full test complete No signs after 28 days

* This information is based on internal testing. For continuous use or advice on product specification with respect to condensation control or temperatures below -80°C, please contact your local T-FIT® representative. Test reports can be made available upon request.



**Hygiene Flex
straights**

**Hygiene Flex
90° Elbow**

Hygiene Flex Tee



Exclusion of Liability

Any information contained in this document is, to the best of the knowledge and belief of Zotefoams plc and of Zotefoams Inc. (together herein referred to as ZOTEFOAMS), accurate. Any liability on the part of ZOTEFOAMS or any subsidiary or holding company of ZOTEFOAMS for any loss, damage, costs or expenses directly or indirectly arising out of the use of such information or the use, application, adaptation or processing of any goods, materials or products described herein is, save as provided in ZOTEFOAMS' conditions of sale ("Conditions of Sale"), hereby excluded to the fullest extent permitted by law.

Where ZOTEFOAMS' goods or materials are to be used in conjunction with other goods or materials, it is the responsibility of the user to obtain from the manufacturers or suppliers of the other goods or materials all technical data and other properties relating to those other goods or materials. Save as provided in the Conditions of Sale no liability can be accepted in respect of the use of ZOTEFOAMS' goods or materials in conjunction with any other goods or materials.

Where ZOTEFOAMS' goods or materials are likely to come into contact with foodstuffs or pharmaceuticals, whether directly or indirectly, or are likely to be used in the manufacture of toys, prior written confirmation of compliance with relevant legislative or regulatory standards for those applications may be requested from ZOTEFOAMS, if appropriate. Save as provided in the Conditions of Sale no liability can be accepted for any damage, loss or injury directly or indirectly arising out of any failure by the user to obtain such confirmation or to observe any recommendations given by or on behalf of ZOTEFOAMS.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

Zotefoams plc Management systems are covered by the following:



Zotefoams plc

675 Mitcham Road, Croydon, Surrey
CR9 3AL, United Kingdom
Tel: +44 (0) 20 8664 1600
Email: t-fitsales@zotefoams.com

T-FIT Insulation Solutions India Private Limited

810 Shapath V, S.G. Highway
Ahmedabad, Gujarat, 380015
Tel: +91 9979867725
Email: t-fitindia@zotefoams.com

Zotefoams T-FIT Material Technology (Kunshan) Co., Ltd

181 Huanlou Road, Development Zone,
Kunshan City, Jiangsu Pr. China 215333
Tel: +86 (0) 512 5012 6001-8001
Email: t-fitchina@zotefoams.com

Zotefoams Inc.

55 Precision Drive
Walton KY, 41094 USA
Tel: +1 (0) 859 371 4025
Free: (800) 362-8358 (US Only)
Email: t-fitusa@zotefoams.com